


Prestressed Concrete Inverted Tee Beam 40IT28-A (Special)

PHYSICAL PROPERTIES

A = 904 in. ²	S _b = 4,551 in. ³
I = 55,827 in. ⁴	S _t = 3,549 in. ³
Y _b = 12.27 in.	Wt. = 942 PLF
Y _t = 15.73 in.	



DESIGN DATA

1. Precast Strength @ 28 days = 7,500 PSI
2. Precast Strength @ release = 5,000 PSI.
3. Precast Density = 150 PCF
4. Strand = 0.60"Ø 270K Lo-Relaxation.
5. Ultimate moment capacity shown below is for full strand development & tension controlled section.
6. Maximum bottom tensile stress is $12\sqrt{f_c} = 1,039$ PSI
7. Flexural strength capacity is based on stress/strain strand relationships and is slightly variable.
8. Deflection limits were not considered when determining allowable loads in this table.
9. All superimposed live loads listed are controlled by ultimate flexural strength, not allowable stresses.
10. All superimposed load is treated as live load in the flexural strength analysis. To determine the allowable live load if the amount of superimposed dead load is known use the following conversion method...

$$\text{Allowable Live Load} = \frac{(1.6)(\text{Load Table Value}) - (1.2)(\text{Superimposed Dead Load})}{1.6}$$

11. If the above conversion is used then allowable stress limits must be checked so they are not exceeded.

ALLOWABLE SUPERIMPOSED LIVE LOADS (KLF)																	
Strand Pattern	Bottom Bars	Top Bars	Moment Capacity	SPAN													
				34'	36'	38'	40'	42'	44'	46'	48'	50'	52'	54'	56'	58'	60'
16 - 12 - 0	None	12 - #9	30,233 "k	9.8	8.7	7.9	7.0	6.4	5.7	5.2	4.7	4.3	3.9	3.6	3.3	3.0	2.7
Strands Debonded At Each End For Length Of →				4 @ 6.0'		4 @ 4.0'		4 @ 1.5'									