


Prestressed Concrete LEDGER BEAM 32LB28

PHYSICAL PROPERTIES

A = 788 in. ²	S _b = 3,878 in. ³
I = 50,443 in. ⁴	S _t = 3,364 in. ³
Y _b = 13.00 in.	Wt. = 821 PLF
Y _t = 15.00 in.	



DESIGN DATA

1. Precast Strength @ 28 days = 6,000 PSI.
2. Precast Strength @ release = 4,000 PSI.
3. Precast Density = 150 PCF.
4. Strand = 0.60"Ø 270K Lo-Relaxation.
5. Ultimate moment capacity shown below is for full strand development & tension controlled section.
6. Maximum bottom tensile stress is $12\sqrt{f'_c} = 930$ PSI.
7. Flexural strength capacity is based on stress/strain strand relationships and is slightly variable.
8. Deflection limits were not considered when determining allowable loads in this table.
9. All superimposed live loads listed are controlled by ultimate flexural strength, not allowable stresses.
10. All superimposed load is treated as live load in the flexural strength analysis. To determine the allowable live load if the amount of superimposed dead load is known use the following conversion method...

$$\text{Allowable Live Load} = \frac{(1.6)(\text{Load Table Value}) - (1.2)(\text{Superimposed Dead Load})}{1.6}$$

11. If the above conversion is used then allowable stress limits must be checked so they are not exceeded.
12. The concrete strength at release of prestress force increases to 4,500 psi for more than 18 strands.
13. Load values to the left of the solid line are controlled by torsional section property limits.
14. Load values to the right of the solid line are controlled by ultimate moment capacity.

ALLOWABLE SUPERIMPOSED LIVE LOADS (KLF)

Strand Pattern	Top Bars	Moment Capacity	SPAN													
			16'	18'	20'	22'	24'	26'	28'	30'	32'	34'	36'	38'	40'	42'
8 - 0 - 0	2 - #9	10,150 "k	13.1	10.6	8.9	7.3	6.6	5.6	4.7	4.0	3.5	3.0	2.6	2.3	2.0	1.7
13 - 0 - 0	4 - #9	15,948 "k	18.3	15.6	14.1	11.9	10.7	9.2	7.8	6.7	5.8	5.1	4.5	3.9	3.5	3.1
13 - 2 - 0	4 - #9	17,900 "k	18.4	16.0	14.2	12.5	11.5	10.4	8.8	7.6	6.6	5.8	5.1	4.5	4.0	3.6
13 - 6 - 0	6 - #9	21,927 "k	18.7	16.3	14.4	12.9	11.7	10.7	9.8	9.1	8.3	7.2	6.4	5.7	5.0	4.5